

Supra UV Bronzefarben zwei Komponenten

Supra UV Metallic inks two pack

Bezeichnung

Supra UV Gold und Silberfarben
zweikomponentig

Einsatzbereich

Bogenoffset, Buchdruck

Eigenschaften

- UV-härtend
- gute Deckkraft
- gute Scheuerfestigkeit
- sehr hoher Metallglanz
- sehr gute Haftung

Bedruckstoffe

Papier, Karton
Kunststofffolien: PVC, PET, PS, PE, PP
(ggf. mit Druckvorbehandlung)

Qualitätsmerkmale

- stabiles Farb- und Feuchtwertsverhalten
- schnelle Härtungsgeschwindigkeit
- gute Transfereigenschaften
- nebelarm

Verarbeitung

Pasten und Firnisse werden getrennt geliefert und müssen direkt vor dem Druck angemischt werden. Die für die Herstellung von UV-Bronzefarben benötigten Anteilungsmittel können beim Einsatz von EPDM-Walzen zum Quellen führen. Gute Beständigkeiten zeigen Mischbezüge auf Basis von NBR.

Einsatzbeschränkungen

Die Farben werden nicht für das Bedrucken von Lebensmittelverpackungen empfohlen!

Lagerung

Produkt kühl und trocken. Die Lagergarantie beträgt 6 Monate.

Description

Supra UV Gold and silver inks
two pack

Application

Sheet-fed offset, letterpress printing

Properties

- UV curing
- good opacity
- good rub resistance
- very high metal effect
- very good adhesion

Substrates

Paper, board
Plastic films: PVC, PET, PS, PE, PP
(if necessary with pre-treatment)

Quality characteristics

- stable ink and dampening behavior
- quick curing speed
- gute Transfereigenschaften
- low misting

Processing

Paste and varnish are separate supplied and must be mixed before printing. The used pasting agent for the manufacture of UV metallic inks can lead to swelling of EPDM rollers. Mixed surfaces based on NBR show a good rub resistance.

Restriction

These inks are not recommended for printing food packaging.

Storage

Product should be stored cool and dry in a dark place. Shelf life in unopened tins is 6 months.

Diese Technische Information hat beratenden Charakter und entspricht unserem derzeitigen Kenntnisstand.

1/2

This technical information has only an advisory character and complies with our current state of knowledge.

Status/ State

04/14

Jänecke+Schneemann
Druckfarben



... natürlich
umweltgerecht

Supra UV Bronzefarben zwei Komponenten

Supra UV Metallic inks two pack

Echtheiten nach DIN ISO 2836 Resistances according to DIN ISO 2836

| Bezeichnung Description | Empfohlenes Mischungsverhältnis Recommended mixing ratio | Artikelnummer Product code | Licht WS nach DIN 16525 light WS acc. to DIN 16525 | lasierend/deckend transparent/opaque | Spirit spirit | Lösemittelgemisch nitro | Alkali alkali |
|--|---|-------------------------------|---|---|------------------|----------------------------|------------------|
| Supra UV Silberfirnis Supra UV Silver varnish | 80 % | 541818 | | | | | |
| Supra UV Goldfirnis Supra UV Gold varnish | 60 % | 554032 | | | | | |
| Supra UV Silberpaste Supra UV Silver paste | 20 % | 541801 | 7 | d o | + | + | - |
| Supra UV Reichgoldpaste Supra UV Rich gold paste | 40 % | 565606 | 5 | d o | + | + | - |
| Supra UV Reichbleichgoldpaste Supra UV Rich pale gold paste | 40 % | 554030 | 5 | d o | + | + | - |
| Supra UV Bleichgoldpaste Supra UV Pale gold paste | 40 % | 567407 | 5 | d o | + | + | - |

Diese Technische Information hat beratenden Charakter und entspricht unserem derzeitigen Kenntnisstand.

2/2

This technical information has only an advisory character and complies with our current state of knowledge.

Status/ State

04/14

**Jänecke+Schneemann
Druckfarben**



... natürlich
umweltgerecht